



PRIOR PLASTIC CO., LTD.

B2,Zhonghua Industrial Zone, Minzhi Street, Longhua, Shenzhen,China
 www.priorplastic.com info@priorplastic.com
 Tel:+86-13760405957

Bakelite(Orange&Black)Technical Data Sheet			
PROPERTIES	Method of Verification	Unit	Value
<i>I.Physical Properties</i>			
Density	ISO 1183	g/cm3	1.40
Water absorption 24hrs	ISO 62	%	<1.6
<i>II.Thermal Properties</i>			
Max. service temperature -Short term	ISO 75-2	°C	300
Max. service temperature - Long term	ISO 75-2	°C	140
Heat deflection temperature-HDT/A	ISO 75-2	°C	150
Coefficient of liner thermal expansion	ISO 11359	10 ⁻⁴ *K ⁻¹	10
Thermal Conductivity	ISO 11359	W/(K*m)	/
Flammability	UL 94	Class	HB
<i>III.Mechanical Properties</i>			
Tensile strength at yield	ISO 527-2	MPa	≥100
Tensile strength at break	ISO 527-2	Mpa	/
Hardness Rockwell	ISO2039-2		115~118
Hardness Shore-D	DIN 53505		98
Impact strength	ISO 179	kJ/m2	67
Bending Strength	ISO 527-2	Mpa	≥120
Elongation at break	ISO 527-2	%	≥0.03
Warping Degree	ISO 179	‰	<0.3
<i>IV.Electrical Properties</i>			
Volume resistivity	IEC 60093	Ohm (Ω) * cm	10 ⁷ ~10 ⁸
Surface resistivity	IEC 60093	Ohm (Ω)	≥1. 0x10 ³
Breakdown Voltage-CW	VDE 0303	kV	10
Arc resistance	VDE 0303	S	/
NOTE: 1 g/cm3 = 1,000 kg/m3, 1 Mpa = 1 N/mm2, 1kV/mm = 1 MV/m			

Statement:

Property data contained herein are typical values of resin for your reference and comparison purposes only. PRIOR will not provide any legally binding guarantee of certain properties, or any suitability.